

Brand Name:

DMMCOAT90

Type of Product: Light Weight Tundish Coating Mass

Chemical Analysis (%)

MgO	SiO ₂	CaO	Fe ₂ O ₃	Al_2O_3
88-90	5.5	3.4	1.4	0.6

Physical Properties

Raw Material Basis	Magnesia
Max Service Temperature(°C)	1620
Bulk Density after drying at 110°C (Kg/m ³)	>2700
Grain Size (mm)	0 -1

All date subject to reasonable deviations, and therefore, should not be used for specification purposes.

ASTM Test Methods, where applicable, used determination of data.

Address: 304 No, 48 Seyedrazi, Mashhad, Iran Factory: Industrial City, Kalat Road, Mashhad www.partodadmehr.com Tel: 051-360 343 66 Telfax: 051-360 340 99